





AS 63 NORUST ZINCTAPE

Versatile and easily applied corrosion control coating system that protects structures from rust.

www.a-spe.com

AS 63 NORUST ZINC TAPE



NoRust Zinc Anti-corrosive Tape is a flexible and self-adhesive material composed of the high-purity zinc mass, special adhesive layer and release liner. It has been designed to ensure anti-corrosive protection for metal elements made of steel, iron and light alloys.

The adhesive layer of NoRust Zinc Tape has a special composition that combines glue and zinc powder to provide electro-conductive properties. **This ensures that zinc is in constant electrical contact with the protected metal.** Properly installed NoRust-Zinc Tape offers a long time protection which, in most situations, will last for the lifetime of the protected object.



TWO OPTIONS AVAILABLE

NON-ELECTRO CONDUCTIVE Only passive protection.

This version of the product is equipped with a regular adhesive without electro conductive properties. It offers **only a PASSIVE protection**, as zinc layer creates a barrier coating on the protected surface.



ELECTRO CONDUCTIVE

Passive and active protection. This version of the product is equipped with special electro conductive adhesive. It offers a double anti-corrosive protection, both PASSIVE and ACTIVE, as the zinc in combinations with the electro-conductive adhesive acts as a sacrificial anode corroding instead of the protected element.

TECHNICAL DETAILS

* without/ with electro-conductive

Zinc layer thickness	100 µm
Adhesive layer thickness	50 / 60 µm *
Total thickness	220 µm (including release liner)
Operating temperature	From -25°C to 120°C (short time 160°C)
DC Resistance	49,2 mΩ ± 2,0 mΩ
Adhesive	water-based acrylic
Adhesive strength	22 N/25mm after 24h (AFERA 5001)
Shelf life	Undefined

APPLICATION FIELDS

- O Industrial tanks and pipelines (refineries and petrochemical plants)
- O Automotive and transport industry (cars, planes, trains, ships, bridges)
- O Marine industry (onshore and offshore)
- O Hinges and bolted connections

INSTALLATION

- The surface must be dry and free from corrosion
- Surface with visible light or medium corrosion needs to be cleaned by mechanical or manual wire brushing.
- In order to achieve an optimum functionality of NoRust Zinc tape it is important to ensure direct contact between NoRust Zinc Tape and steel.
- Do not apply NoRust Zinc Tape when the air or metal temperate is less than 3°C or within 3°C of the dew point.
 Exposure temperature should be between -40 and +160°C.

INTALLATION

Zinc Tape is applied directly onto the steel structure. During the installation on flat surfaces, apply the tape on the whole surface with an overlap of a minimum 20 mm. To protect irregular shapes, Zinc tape needs to be cut to the required dimension. Apply the tape carefully to avoid air bubbles or creases. Very good adhesion is achieved by using magnetic roller applicator. The application of NoRust Zinc Tape on pipes is the fastest and most efficient when carried out by a wrapping machine. Otherwise, Zinc Tape needs to be cut and hand-applied.

AVAILABILITY

	ER HONS STOM SES ICIAL ND
AS-63/100	673523
AS-63/50	673522
AS-63/25	673221
CODE	IMPA
CODE	I



A-SPE EUROPE SP. J. Agatowa 5, 82-310 Gronowo Górne, Poland, +48 55 236 77 36, www.a-spe.com, info@a-spe.com

www.a-spe.com